

Amendments to the Claims

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims

1. (Withdrawn) An apparatus to provide hemostasis at a blood vessel puncture site, comprising:
 - a hemostasis material; and
 - a clot formation accelerator, wherein said clot formation accelerator is substantially dispersed throughout said hemostasis material.
2. (Withdrawn) The apparatus of claim 1 wherein said clot formation accelerator is a clot agglomeration.
3. (Withdrawn) The apparatus of claim 1 wherein said clot formation accelerator is Chitosan.
4. (Withdrawn) The apparatus of claim 1 wherein said clot formation accelerator is a thrombogenic agent.
5. (Withdrawn) The apparatus of claim 4 further comprising a polysaccharide.
6. (Withdrawn) The apparatus of claim 6 wherein said polysaccharide is Chitosan.
7. (Withdrawn) An apparatus to provide hemostasis at a blood vessel puncture site, comprising:
 - a hemostasis material;

a clot formation accelerator; and
a polysaccharide,
wherein said clot formation accelerator and said polysaccharide are substantially dispersed throughout said hemostasis material.

8. (Withdrawn) The apparatus of claim 7 further comprising a cross-linking agent.

9. (Withdrawn) The apparatus of claim 7 wherein said clot formation accelerator is a thrombogenic agent.

10. (Withdrawn) The apparatus of claim 7 wherein said polysaccharide is Chitosan.

11. (Withdrawn) An apparatus to provide hemostasis at a blood vessel puncture site, comprising:
a hemostasis material;
a cross-linking agent;
a polysaccharide; and
a clot formation accelerator,
wherein said cross-linking agent, said clot formation accelerator, and said polysaccharide are substantially dispersed throughout said hemostasis material.

12. (Withdrawn) The apparatus of claim 11 wherein said clot formation accelerator is a thrombogenic agent.

13. (Withdrawn) The apparatus of claim 11 wherein said polysaccharide is Chitosan.

14. (Withdrawn) The apparatus of claim 11 wherein said cross-linking agent is a formaldehyde.

15. (Withdrawn) A method for forming a clot formation accelerator loaded hemostasis material, comprising:
heating gelatin granules in water;
adding a cross-linking agent;
mixing a clot formation accelerator to the cross-linking agent and heated gelatin solution; and
adding air to form a gelatin foam hemostasis material matrix,
wherein said clot formation accelerator is substantially dispersed throughout said hemostasis material.

16. (Withdrawn) The method of claim 15 wherein said dissolving further comprises adding a polysaccharide.

17. (Withdrawn) The method of claim 16 wherein said polysaccharide is Chitosan.

18. (Withdrawn) The method of claim 16 wherein the clot formation accelerator is a thrombogenic agent.

19. (Withdrawn) The method of claim 15 further comprising drying said gelatin foam hemostasis material matrix above a freezing point temperature.

20. (Withdrawn) A method for forming a clot formation accelerator loaded hemostasis material, comprising:
heating gelatin granules in water;
adding a cross-linking agent;
mixing a clot formation accelerator to the cross-linking agent and heated gelatin solution; and
drying said clot formation accelerator mixture at a temperature above a freezing point temperature to form said hemostasis material,

wherein said clot formation accelerator is substantially dispersed throughout said hemostasis material.

21. (Withdrawn) The method of claim 20 wherein said heating further comprises adding a polysaccharide.

22. (Withdrawn) The method of claim 21 wherein said polysaccharide is Chitosan.

23. (Withdrawn) The method of claim 21 wherein the clot formation accelerator is a thrombogenic agent.

24. (Currently Amended) An apparatus for forming a clot formation accelerator loaded hemostasis material, comprising:

a mixing chamber;

~~means for heating~~ a heat source capable of heating the mixing chamber;

a water supply connected to the mixing chamber;

a granule feeding system capable of feeding gelatin granules in water;

~~means for adding~~ a cross-linking agent addition element;

~~means for mixing a clot formation accelerator~~ addition element to the cross-linking agent and heated gelatin solution;

a mixing element capable of stirring the contents of the mixing chamber; and

~~means for adding an air injector to form a gelatin foam hemostasis material matrix~~ foam the contents of the mixing chamber.

25. (Currently Amended) The apparatus of claim 24 ~~wherein said means for dissolving further comprises adding~~ comprising a polysaccharide addition element.

26-27. (Canceled)

28. (Currently Amended) The apparatus of claim 24 further comprising ~~means for drying a dryer for said foamed contents of the mixing chamber~~ gelatin foam ~~hemostasis material matrix~~ said dryer operating above a freezing point temperature.

29. (Currently Amended) An apparatus for forming a clot formation accelerator loaded hemostasis material, comprising:

a mixing chamber;

a heat source capable of heating the mixing chamber ~~means for heating gelatin granules in water;~~

a water supply connected to the mixing chamber;

a granule feeding system capable of feeding gelatin granules;

~~means for adding~~ a cross-linking agent addition element;

~~means for mixing a clot formation accelerator~~ addition element ~~to the cross-linking agent and heated gelatin solution;~~

a mixing element capable of stirring the contents of the mixing chamber;

an air injector to foam the contents of the mixing chamber; and

~~means for drying a dryer for the contents of the mixing chamber~~ said clot formation accelerator mixture said dryer operating at a temperature above a freezing point temperature to form a foam ~~said hemostasis material;~~

~~wherein said clot formation accelerator is substantially dispersed throughout said hemostasis material.~~

30. (Currently Amended) The apparatus of claim 29 ~~wherein said means for heating further comprises adding~~ further comprising a polysaccharide addition element.

31-32. (Canceled)